



BQ	Material: R780,pipe body hardness HRC28-32,threading surface hardness HRC40-50 yield strength 850Mpa, tensile strength 1010Mpa, elongation 17.2%
NQ	
HQ	
Double Heat Treated rods. First full length heat treatment, quenching & tempering. Second, out surface coating for threading to make higher hardness	
Tolerance on 3m rod's length +/- 3 mm	
Bundle : 20 rods	

